

NORBORNENE COMPOUND CONTAINING CHAIN POLYENE GROUP AND ITS PRODUCTION, UNSATURATED ETHYLENIC COPOLYMER USING THE SAME AND ITS PRODUCTION, AND RUBBER COMPOSITION CONTAINING THE SAME COPOLYMER

Patent Number: JP9040586

Publication date: 1997-02-10

Inventor(s): ISHIDA TATSUKAZU; YASUDA MASAOKI; ONISHI HITOSHI; KIHARA NORIAKI; TSUTSUI TOSHIYUKI; AINE TOSHIHIRO; KAWASAKI MASAOKI; NAKAHAMA HIDENARI

Applicant(s): MITSUI PETROCHEM IND LTD

Requested

Patent: 特 JP9040586

Application

Number: JP19950339668 19951226

Priority Number
(s):

IPC

Classification: C07C13/43 ; C07C2/50 ; C08L21/00

EC

Classification:

Equivalents:

Abstract

PROBLEM TO BE SOLVED: To obtain a new norbornene compound containing a chain polyene group, excellent in weather resisting, heat resisting and ozone resisting properties, having a rapid vulcanization rate, and capable of suitably being used for the production of the unsaturated ethylenic copolymer useful for an automobile part such as a brake part, and a heat insulating material, etc.

SOLUTION: This norbornene compound is a compound of formula I [$R<1>$ is a 1-5C alkyl; $R<2>$, $R<3>$ are each H or $R<1>$; (n) is 1-5], e.g. 5-(2-ethylidene-6-methyl-5-heptenyl)-2-norbornene. The compound of the formula I is obtained by reacting (A) a compound of formula III obtained by reacting ethylene with a compound of formula II in the presence of a catalyst consisting of a transition metal compound and an organic aluminum compound, with (B) cyclopentadiene.

Data supplied from the esp@cenet database - I2